

Some data good to have when evaluating the run:

Sample material: wood

The ingoing weight in run 6607 was 43.8 mg

The weight of the residue was 0.3 mg

The sample lowering time was 11.4 s

The time it took after the sample was lowered to getting the first reading on the balance display was 21 s

The gas going through the reactor: 40% H₂O and 60% N₂

The total flow was 2 l/min (do not include the purge He)

The total pressure was 1 bar